

Product Information Sheet



ElectroSpense™ D-132 silver conductor pastes are rheologically stable, easy-to-process materials, designed for screen printing of electrodes and conductive traces on glass or other high-temperature substrates.

Product Benefits

- Lead-free
- Excellent adhesion to ITO or F-doped Tin Oxide
- Ideal for printing fine features
- Tailored conductivity
- Ease of processing

Typical Properties

ElectroSpense conductor pastes are characterized by exceptional fineness of grind and particle size uniformity. Target resistivities can be realized over a broad range of firing temperatures.

Typical Properties	D-132
Resistivity (mΩ/sq @ 1 mil)	2.8-3.8
Fired Thickness (μm) ¹	5-8
Viscosity (kcps) ²	75 ± 30
Peak Firing Temp ³ (°C)	475 ± 25
Time at Peak (min)	5-20
Adhesion ⁴	Pass

(1) Wet thickness 22-26 μm.

(2) Measured with Brookfield R/S Rheometer, 25 mm cone/plate @ 9.6 s⁻¹, 25°C.

(3) Air dried 3-4 minutes and 90 to 110°C for 10-15 minutes before firing.

(4) Scotch tape adhesion test.

Processing Recommendations

Application: Screen printing

Screen Type: 325 mesh stainless steel

Typical Line Resolution: 100-125 μm (4-5 mils); no line spreading upon drying. Finer resolution is achieved under select conditions.

Paste Storage & Shelf Life: The paste should be stored in tightly capped containers, in a cool, dry place away from direct sunlight. Properly stored material will have a shelf life in excess of 6 months.

Thinning: Thinning is not recommended since the paste is supplied at the correct viscosity for application. Thinning may become necessary to replace solvent lost by evaporation. Contact Five Star for appropriate solvent choices.

Applications

Bus electrodes for display formats involving rigid substrates.



6801 Brecksville Road, Suite 200, Independence, OH 44131 | 877-513-3483 | Fax 216-447-9424 | www.fivestartech.com

While the information and recommendations included in this document are believed to be accurate, nothing contained herein is to be construed as a representation of a warranty of merchantability or fitness for any particular purpose. Buyer is responsible to determine the applicability of such information and recommendations for its own particular purpose, and to ensure that its intended use of the Product does not infringe any intellectual property rights.